

MATERIAL	HARDNESS
ASTM A 182 F 1	≤ 150 HB
ASTM A 182 F 5	≤ 150 HB
ASTM A 182 F 11/F12	≤ 150 HB
ASTM A 182 F 22 CLASS 3	≤ 150 HB
ASTM A 182 F316L	≤ 160 HB
ASTM A 182 F316	≤ 160 HB
ASTM A 182 F316Ti	≤ 160 HB
ASTM A 182 F304	≤ 160 HB
ASTM A 182 F304L	≤ 160 HB
ASTM A 182 F321	≤ 160 HB
ASTM A 182 F347	≤ 160 HB
ASTM A 182 F310 MoLn	≤ 170 HB
ASTM A 182 F 51	≤ 195 HB
ASTM A 182 F 44	≤ 180 HB
ASTM B 381 F1	≤ 140 HB
ASTM B 381 F2	≤ 150 HB
ASTM B 381 F3	≤ 160 HB
ASTM B 649 UNS N08904	≤ 150 HB
ASTM B 564 UNS N06625	≤ 195 HB
ASTM B 564 UNS N08825	≤ 175 HB
ASTM B 564 UNS N04400	≤ 150 HB
ASTM B564 UNS N08800	≤ 160 HB
ASTM B564 UNS N08810	≤ 160 HB
ASTM B564 UNS N08811	≤ 160 HB
ASTM A 182 F51 UNS S31803	≤ 190 HB
ASTM A 182 F53 UNS S32750	≤ 250 HB
ASTM A 182 F55 UNS S32760	≤ 250 HB

**Si garantisce solo il valore della durezza le altre caratteristiche non verranno verificate
ne certificate.**

We can guarantee only hardness test ,no others testing shall be performed and certified.

INOXFUCINE SpA.

g. foletti